M 19 HR Primary Li-MnO₂ cell

3 V high power lithium manganese dioxide short D-size spiral cell

Saft's M 19 HR cell is ideally suited for applications requiring high discharge, continuous or pulse power with stable voltage in - 40°C /+ 72°C environment.

Benefits

- High drain / high pulse capability
- High voltage response, stable during most of the lifetime of the application even after long dormant periods
- High capacity at high current and low temperature
- Low self-discharge compatible with long operating life (less than 1% after 1 year of storage at + 20°C)
- Superior resistance to corrosion
- Low magnetic signature

Key features

- Spiral construction
- Hermetic construction with glass-to-metal seal
- Stainless steel container
- Integrated safety vent
- Non-corrosive electrolyte
- Non-pressurized at room temperature
- Restricted for transport (Class 9)
- Made in Germany

Designed to meet all major quality, safety and environmental standards

- Safety: UL 1642 (File MH 12609)
- Transport: UN 3090 and UN 3091
- Military: VG96915 part 2 and part 154
- Quality: ISO 9001, Saft World Class Continuous program
- Environment: ISO 14001

Typical applications

- Radio communications
- Alarms and security systems
- ELTs, EPIRBs
- Tracking systems
- M2M communication
- Medical devices



| Electrical characteristics | |
|--|--------------|
| (Typical values relative to cells stored up to one year at + 30°C max) | |
| Nominal capacity (at 500 mA, + 20°C, 2.0 V cut-off) [1] | 10.3 Ah |
| Open circuit voltage (at + 20°C) | 3.2 V |
| Nominal voltage (under 1 mA at + 20°C) | 3.0 V |
| Nominal energy (at 500 mA, + 20°C, 2.0 V cut-off) | 29 Wh |
| Pulse capacity (2) | up to 10.0 A |
| Recommended maximum continuous discharge current (3) | 4.0 A |
| | |

| Operating conditions | | |
|--------------------------|--------------------|-------------------------------------|
| Operating temperature ra | nge ^[4] | - 40°C / + 72°C (- 40°F / + 161°F) |
| Storage temperatures | Recommended | + 30°C (+ 86°F) max |
| | Allowable (5) | - 55°C to + 85°C (- 67°F / + 185°F) |

| Physical characteristics | |
|--|-------------------|
| Diameter (max) | 33.5 mm (1.32 in) |
| Height for the tabbed version (max) | 58.5 mm (2.30 in) |
| Height for the version with +/- end caps (max) | 59.5 mm (2.34 in) |
| Typical weight | 107 g |
| Li metal content | approx. 3.3 g |

^[1] Dependent upon current drain, temperature and cut-off.

thermal protection. Consult Saft.




^[2] Dependent upon pulse characteristics, temperature, cell history and application. Higher rates are available under certain circumstances ^[3] To maintain cell heating within safe limits. Battery packs may imply lower level of maximum current and may request specific


⁽⁴⁾ Operating temperatures up to + 85°C can be achieved. Consult Saft.

^[5] Long time storage at high temperature may affect performances. Consult Saft.

Termination & part numbers

- 1. + tab (radial tab on positive terminal): 4142250403
- 2. C tab (radial tabs on positive & negative terminals) 4142250203
- 3. Z tab (radial tabs on positive & negative terminals): 4142250703
- 4. +/- end caps (incl. PTC): 4142257103
- Other configuration available on request







Storage


■ The storage area should be clean, cool (preferably not exceeding + 30°C), dry and ventilated.

Warning

- Fire, explosion and burn hazard.
- Do not recharge, short circuit, crush, disassemble, heat above + 100°C (+ 212°F), incinerate, or expose contents to water.
- Do not solder directly to the cell (use tabbed cell versions instead).
- Do not obstruct venting mechanism.









Saft

12, rue Sadi Carnot 93170 Bagnolet - France

Tel.: +33 1 49 93 19 18 Fax: +33 1 49 93 19 64 www.saftbatteries.com

Friemann & Wolf Batterietechnik GmbH

Industriestr. 22, 63654 Büdingen - Germany Tel.: +49 (0) 6042 954 0 Fax.: +49 (0) 6042 954 190

Doc N°: 31115-2-1014

Edition: October 2014

Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft.

Published by the Communications Department

Photo credit: Saft

Produced in FR by Soyouzgraphic